





Technical Characteristics

Presentation

Viscosity	Products		ISO 4823 ADA 19	Oral setting time (min.)	Total setting time	Strain in compression (min-max)	Shore-A hardness	Presentation
Putty	Hard		Type 0 Putty Consist.	3 min. 30 sec	5 min. 30 sec	1-3%	70+/-2	280 ml jar of base 280 ml jar of catalyst
	Soft		Type 0 Putty Consist.	3 min. 30 sec	5 min. 30 sec	1-3%	60+/-2	
	Soft Fast set		Type 0 Putty Consist.	2 min. 30 sec	4 min.	1-3%	60+/-2	
	Super Soft Fast set		Type 0 Putty Consist.	2 min. 30 sec	4 min.	1-3%	60+/-2	
Medium	Tray material		Type 1 Heavy-bodied Consist.	2 min. 30 sec	4 min.	3-5%	60+/-2	2 x 380 ml cartridges, 2 x locking rings, 20 x dynamic mixing tips
	Regular		Type 2 Medium-bodied Consist.	3 min. 30 sec	5 min. 30 sec	3-5%	45+/-2	2 x 50 ml cartridges, 12 mixing tips
Light	Light		Type 3 Light-bodied Consist.	3 min. 30 sec	5 min. 30 sec	3-5%	45+/-2	2 x 50 ml cartridges, 12 mixing tips
	Super Light		Type 3 Light-bodied Consist.	3 min. 30 sec	5 min. 30 sec	3-5%	45+/-2	
	Light Fast set		Type 3 Light-bodied Consist.	2 min. 30 sec	4 min.	3-5%	45+/-2	